



# TimeSaver SR

## Ultra High Solids Finish

TimeSaver SR Ultra High Solids Finish is an ultra-high solids scrub and recoat finish that saves time and money.

### Features & Benefits

- Provides excellent initial gloss and gloss retention, even with fewer coats
- Requires fewer initial coats and typically only one coat when recoating to achieve a high gloss appearance level
- Exceptional resistance to scratching, scuffing and black heel marks
- Solids content 30%
- Meets ASTM D-2047 slip resistance requirements

### Applications

- For use on resilient and most hard surface flooring. A sealer may be required for highly polished stone surfaces, glazed ceramic tile, luxury vinyl tile and some rubber floors
- Not intended for use on cork, wood, or bamboo flooring
- Ideal for use in patient rooms, busy hallways, aisles and 24-hour facilities



SHIP AND WAREHOUSE THIS SIDE UP  
EMBARQUE Y ALMACENE EN LA BODEGA CON ESTE LADO HACIA ARRIBA



# TimeSaver SR

## Ultra High Solids Finish

### Use Instructions

- Blockade areas to be stripped or finished. Floors will be very slippery until dry.
- Strip floor using a Diversey stripper per the instructions on the stripper label

### Coating

- Using a clean mop, apply a maximum of 3 medium coats of TimeSaver SR Ultra High Solids Finish. After 24 hours, additional coats may be applied until desired gloss is achieved.
- Allow 30–40 minutes drying time between coats. Temperature, humidity and ventilation may affect drying time. Allow finish to cure for 24 hours before burnishing or applying extra coats. Apply no more than 3 coats in a 24-hour period.

### Maintenance

- Dust mop or sweep
- Clean the floor with a mop or an automatic scrubber using the recommended Diversey brand cleaner according to label directions
- To enhance appearance, use any of the following methods: Spray Buff with Diversey brand spray buff, a red pad and 175–1500 rpm equipment. Dry buff using a medium to aggressive pad and 1000–1500 rpm equipment. Ultra-high speed burnish using a medium to aggressive pad and 2000 rpm equipment.

### Recoating

- Dust mop or sweep
- Clean the floor with a mop or an automatic scrubber using the recommended Diversey brand cleaner according to label directions
- Blockade area and apply 1–2 uniform coats of finish using a clean mop. Allow finish to cure for 24 hours before burnishing.

Technical data	TimeSaver SR
Color/Form	Milky White, Liquid
pH	8.5
Scent	Ammonia
Shelf Life	2 Years

Product	Pack size	Dilution	Product code	
TimeSaver SR	4 x 1 gal. / 3.78 L Containers	Ready-to-use	3137723	
TimeSaver SR	1 x 5 gal. / 18.9 L Envirobox <sup>TM/MC</sup>	Ready-to-use	5104984	

### Safe handling

Please make sure your employees read and understand the product label and Safety Data Sheet before using this product. The label contains directions for use; and both the label and SDS contain hazard warnings, precautionary statements and first aid procedures. SDS are available online at [www.diversey.com](http://www.diversey.com) or by calling 888.352.2249. Improper use or dilution may result in damage to surfaces and may result in health and physical hazards that match those of the concentrate.