

White Food Grade with PTFE

Product Description

Never-Seez® White Food Grade with PTFE is a premium quality lubricant composed entirely of ingredients which meet FDA requirements where incidental food contact is possible. It has been approved by the U.S. Department of Agriculture for use in establishments operating under the Federal Meat and Poultry Products Inspection Program. The unique dispersion of FDA authorized PTFE provides additional lubricity especially where a thin film of lubricant is desirable. Never-Seez White Food Grade with PTFE is virtually odorless, colorless, and tasteless. It is a "multi-purpose" lubricant for varied services within a food handling plant.

Product Benefits

- Provides maximum lubrication up to 475°F
- Keeps parts working longer with less wear
- Prevents rust and corrosion
- Resists water and chemical washout
- Non-staining
- Provides a seal against entrance of liquids in bearings
- Suitable for pipe threads used with potable water—will not impart an odor or taste

Product Applications

- Nuts, bolts, screws
- Pipe fittings
- Stainless steel fittings
- Valve stems and assemblies
- Pump gears
- Chain drives
- Gaskets
- Press fit assemblies
- Conveyor and oven bearings
- Packaging machinery
- Worm gears
- Slow speed or highly loaded bearings <500 RPM

Limitations

- High speed bearings
- Not approved for continuous contact with food

Other Anti-Seize Lubricants

- Regular Grade
- Pure Nickel Special
- Nuclear Grade, Nickel Special
- High Temp Stainless
- High Temp Stainless, Nuclear Certified
- Marine Grade
- Blue Moly
- Black Moly
- Red Bearing Lubricant
- High Temperature Bearing Lubricant
- Pipe Compound with Teflon®
- Heavy Metal Free

® Teflon is a Registered Trademark of Dupont.



Technical Specifications

Color	White	
Temperature Range, °F (°C)	-5°F to 450°F (-21°C to 232°C)	
Thickener Type	Aluminum Complex	
Particle Size, mil (microns)	2.0 max. (50 µ)	
Density, (g/cm3)	0.91 to 1.03	
	ASTM Test Method	
Flash Point, °F (°C)	430°F (221°C)	D-92
Copper Corrosion Test @ 212°F (100°C), 24 hrs.	1b	D-130
Worked Penetration (60 strokes @ 77°F (25°C)	255-295	D-217
NGLI Grade	2	D-217
Dropping Point, (minimum) °F (°C)	500°F (260°C)	D-566
Torque Coefficient, k factor	0.13	
Water Washout, % loss @ 175°F (79°C)	<5	D-1264
Bearing Rust Test	Pass	D-1743
Timken OK Load, lb.	40	D-2509
Four Ball EP	Load Wear Index	43.7
	Last Non-seizure Load (scar)	63 kgf (0.36 mm)
	Last Seizure Load (scar)	250 kgf (2.42 mm)
	Weld Load	315 kgf

Specifications: Certified NSF H-1

Ingredients: Contains food grade grease, PTFE, and zinc oxide.

Shelf Life: Never-Seez® White Food Grade with PTFE does not deteriorate with age when stored unopened at temperatures below 120°F (49°C). Quality and performance are guaranteed for five years from the date of manufacture on unopened containers.

Use in accordance with Material Safety Data Sheet.

Ordering Information:

NEVER-SEEZ® WHITE FOOD GRADE WITH PTFE

STOCK NUMBER	DESCRIPTION	SIZE
NSWT-14	Flat Top	14 oz.
NSWT-1C	Cartridge for Standard Grease Gun	14.1 oz.
NSWT-7	Flat Top	7 lbs.
NSWT-120B	Drum	120 lbs.
NSWT-400B	Drum	400 lbs.

IMPORTANT NOTICE

All statements, technical information and recommendations set forth herein are based on tests which Bostik, Inc. believes to be reliable. However, Bostik, Inc. does not guarantee their accuracy or completeness. The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. Any sales of this product shall be on terms and conditions set forth on Bostik's order acknowledgment. Bostik, Inc. warrants that the product conforms with Bostik's written specifications, and is free from defects. BOSTIK, INC. DISCLAIMS ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. THE BUYER'S SOLE REMEDY FOR NONCOMPLIANCE WITH THIS WARRANTY SHALL BE FOR THE REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. IN NO CASE WILL BOSTIK, INC. BE LIABLE FOR DIRECT, CONSEQUENTIAL ECONOMIC OR OTHER DAMAGES.

Bostik, Inc.

211 Boston Street
Middleton, MA 01449-2128 USA
Technical Service: 888-603-8558
FAX: 978-750-7293
<http://www.bostik-us.com>

N8-02/08/07